

Technische Daten ROR

Typ Ø mm'	Wandstärke mm'	Gewicht kg/m'	Querschnitt F / mm ²	max. Gebrauchslast	
				St 52 / kN	N 80 / kN
73	7.5	12.1	1542	313	495
73	9	14.2	1808	367	581
88.9	7.5	15.0	1917	389	616
88.9	9	17.7	2258	458	725
88.9	10	19.4	2477	502	795
101.6	8	18.5	2351	477	755
101.6	10	22.6	2876	583	924
114.3	8	21.0	2670	542	857
114.3	9	23.4	2976	604	956
114.3	10	25.7	3275	664	1052
127	9	26.2	3334	676	1071
127	10	28.8	3674	745	1180
139.7	9	29.0	3693	749	1186
139.7	10	32.0	4072	826	1308
168.3	9	35.3	4502	913	1446
168.3	10	39.0	4970	1008	1596
177.8	9	37.4	4770	968	1532
177.8	10	41.4	5269	1069	1692

St 52 Fließspannung = 355 N/mm² F_y
N80 Fließspannung = 562 N/mm² F_y
max. Gebrauchslast = F_y x F : 1.75

andere Ø und Wandstärken können auf Wunsch geliefert werden